NSN 8030-01-564-0189

Sealing Compound - Page 1 of 1



View Online at https://aerobasegroup.com/nsn/8030-01-564-0189

_						
u	rn	~ I) or	ne:
	··	u	u	LIN	aı	HE.

Corrosionbloc sealants

Special Features:

Oleoresinous air dry, lap joint sealants, corrosion and glavanic corrosion preventive. Exposed sealer permits painting while non-exposed sealer remains "wet", flexible and elastic. Specific gravity; 1.39 to 1.45. Solids 88 to 92%. Flash point, seta flash cc 105 to 114 degree f. No sag with 0.25 inch bead. Dry time at 68 degree f; 50% rh: 960hours set to touch. 0.125 inch thick; does not dry through

\sim	I
L.O	IOL:

Yellow

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A536d0