

View Online at <https://aerobasegroup.com/nsn/8030-01-600-7705>

Physical Form:

Liquid

Specific Usage Design:

Secondary fuel barrier on aircraft integral fuel tanks

Curing Method:

Air dried

Rated Drying Time:

Between 2.000 hours and 24.000 hours

Special Features:

Two part solution; viscosity - brookfield no. 5 at 20 rpm, 50 poise

Material:

Plastic polyurethane

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A536d0