

View Online at <https://aerobasegroup.com/nsn/8030-01-614-7593>

Special Features:

Dichromate treatment; provides satisfactory paint base qualities on all standard alloys except ek30a, ek41a, hm31a, hm21a, hk31a, la141a and m1a; applied after machining adds no appreciable dimension changes; 30-45 minute immersion time; steel tank construction

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A535w0