

View Online at <https://aerobasegroup.com/nsn/8030-01-614-7593>

**Special Features:**

Dichromate treatment; provides satisfactory paint base qualities on all standard alloys except ek30a, ek41a, hm31a, hm21a, hk31a, la141a and m1a; applied after machining adds no appreciable dimension changes; 30-45 minute immersion time; steel tank construction

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fiig:**

A535w0