

View Online at <https://aerobasegroup.com/nsn/8030-01-627-1475>

**Physical Form:**

Paste

**Specific Usage Design:**

Fillet sealing of fuel tanks and other aircraft fuselage sealing applications

**Curing Method:**

Air dried

**Features Provided:**

Separate catalyst

**Rated Drying Time:**

14.0 days

**Product Name:**

Low weight fuel tank sealant

**Special Features:**

Low density, high temperature aircraft integral fuel tank sealant; service temperature range from -54 degrees c to 121 degrees c; item is a two-part manganese dioxide cured permapol p-5 modified polysulfide

**Color:**

Brown

**Material:**

Rubber synthetic

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fiig:**

A536d0