

View Online at <https://aerobasegroup.com/nsn/8030-01-648-2182>

Temperature Rating:

-65.0 degrees fahrenheit and 250.0 degrees fahrenheit

Physical Form:

Paste

Quantity Within Each Unit Package:

6.0 ounces

Specific Usage Design:

This material acts as an effective barrier against the common causes of corrosion on the aluminum alloys or between dissimilar metals. The cured sealant maintains elastomeric properties after limited exposure to both jet fuel and aviation gas

Curing Method:

Air dried

Rated Drying Time:

7.0 days

Product Name:

Corrosion inhibitive sealant

Special Features:

Temperature range from -65°F (-54°C) to 250°F (121°C). With intermittent excursions up to 275°F (135°C). Class a is a two-part, manganese dioxide cured polysulfide compound

Color:

Gray

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A536d0