

View Online at <https://aerobasegroup.com/nsn/8040-01-205-3996>

**Tempurature Rating:**

200.0 degrees celsius

**Physical Form:**

Liquid

**Quantity Within Each Unit Package:**

8.000 ounces

**Specific Usage Design:**

For bonding glass lcd and laser windows and for potting fiber optics

**Features Provided:**

Separate catalyst

**Rated Drying Time:**

1.000 hours

**Special Features:**

High temperature resistant; elevated temperature cure, 1 hour at 150 degrees c; service temperature range of minus 55 degrees c to plus 200 degrees c

**Color:**

Amber

**Material:**

Plastic epoxy

**Supplementary Features:**

8 ounce kit

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fiig:**

A535p0