

View Online at <https://aerobasegroup.com/nsn/8040-01-208-6005>

**Physical Form:**

Liquid

**Quantity Within Each Unit Package:**

2.000 grams

**Specific Usage Design:**

For bonding fiber optic and optical materials

**Features Provided:**

Separate catalyst

**Rated Drying Time:**

15.000 minutes

**Special Features:**

Elevated temperature cure; 15 minutes at 100 degrees c or 5 minutes at 125 degrees c or 1 minute at 150 degrees c; service temperature range of minus 60 degrees c to plus 175 degrees c; color changes from light green mixed uncured to clear reddish amber when fully cured

**Color:**

Amber

**Material:**

Plastic epoxy

**Supplementary Features:**

2 gram kit

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fig:**

A535p0