

View Online at <https://aerobasegroup.com/nsn/8040-01-208-6005>

Physical Form:

Liquid

Quantity Within Each Unit Package:

2.000 grams

Specific Usage Design:

For bonding fiber optic and optical materials

Features Provided:

Separate catalyst

Rated Drying Time:

15.000 minutes

Special Features:

Elevated temperature cure; 15 minutes at 100 degrees c or 5 minutes at 125 degrees c or 1 minute at 150 degrees c; service temperature range of minus 60 degrees c to plus 175 degrees c; color changes from light green mixed uncured to clear reddish amber when fully cured

Color:

Amber

Material:

Plastic epoxy

Supplementary Features:

2 gram kit

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fig:

A535p0