

View Online at <https://aerobasegroup.com/nsn/8040-01-356-5174>

Physical Form:

Liquid

Specific Usage Design:

For bonding metals, ceramics, woods and a variety of other materials

Features Provided:

Separate catalyst

Rated Drying Time:

24.000 hours

Special Features:

Room temperature or elevated temperature cure; 24 hours at room temperature, 2 hours at 60 degrees c or 15 minutes at 100 degrees c

Color:

Yellow

Material:

Plastic epoxy

Supplementary Features:

Six 1 quart kits

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A535p0