

View Online at <https://aerobasegroup.com/nsn/8040-01-356-5174>

**Physical Form:**

Liquid

**Specific Usage Design:**

For bonding metals, ceramics, woods and a variety of other materials

**Features Provided:**

Separate catalyst

**Rated Drying Time:**

24.000 hours

**Special Features:**

Room temperature or elevated temperature cure; 24 hours at room temperature, 2 hours at 60 degrees c or 15 minutes at 100 degrees c

**Color:**

Yellow

**Material:**

Plastic epoxy

**Supplementary Features:**

Six 1 quart kits

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fig:**

A535p0