

View Online at <https://aerobasegroup.com/nsn/8040-01-360-8026>

**Physical Form:**

Paste

**Specific Usage Design:**

For casting, edging, caulking and bonding inserts in metal core sandwich panels

**Features Provided:**

Separate catalyst

**Rated Drying Time:**

24.000 hours

**Special Features:**

Thixotropic; room temperature cure or elevated temperature cure; 16 to 24 hour cure at 77 degrees f, 3 hours at 165 degrees f, 1 hour at 200 degrees f

**Color:**

Amber

**Material:**

Plastic epoxy

**Supplementary Features:**

1 quart resin and 1 quart hardener

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fig:**

A535p0