NSN 8040-01-360-8026

View Online at https://aerobasegroup.com/nsn/8040-01-360-8026

Physical Form:

Paste

Specific Usage Design:

For casting, edging, caulking and bonding inserts in metal core sandwich panels

Features Provided:

Separate catalyst

Rated Drying Time:

24.000 hours

Special Features:

Thixotropic; room temperature cure or elevated temperature cure; 16 to 24 hour cure at 77 degrees f, 3 hours at 165 degrees f, 1 hour at 200 degrees f

Color:

Amber

Material:

Plastic epoxy

Supplementary Features:

1 quart resin and 1 quart hardener

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A535p0