

View Online at <https://aerobasegroup.com/nsn/8040-01-362-6767>

Physical Form:

Paste

Specific Usage Design:

Bonding metal to metal and high temp. Performance plastics, continuous service to 500 f, good resistance to thermal shock, resists oils, fuels and many solvents, lap shear strength 2400 psi rt, best properties when cured above 350 f, 2 part, paste and powder, flows when curing, mix contents well in can before using

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A535p0