

View Online at <https://aerobasegroup.com/nsn/8040-01-381-1696>

**Physical Form:**

Paste

**Quantity Within Each Unit Package:**

1.000 pounds

**Specific Usage Design:**

For use in sundstrand corporation vacuum pressure impregnation process

**Features Provided:**

Separate catalyst

**Rated Drying Time:**

3.000 hours

**Special Features:**

Elevated temperature cure, 3 hours at 125 degrees c plus 3 hours at 155 degrees c

**Color:**

Black

**Material:**

Plastic epoxy

**Supplementary Features:**

1 pound kit

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fiig:**

A535p0