

View Online at <https://aerobasegroup.com/nsn/8040-01-381-2258>

Physical Form:

Paste

Quantity Within Each Unit Package:

1.000 gallons

Specific Usage Design:

For bonding aircraft engine hardware

Features Provided:

Separate catalyst

Rated Drying Time:

2.000 hours

Special Features:

Resistant to temperatures up to 1000 degrees f; elevated temperature cure, 2 hours at 140 degrees f, then 1 hour at 175 degrees f, then 1 hour at 200 degrees f, then 2 hours at 360 degrees f; refrigerated storage required

Color:

Gray

Material:

Ceramic

Supplementary Features:

1 gallon kit

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A535p0