

View Online at <https://aerobasegroup.com/nsn/8040-01-388-0735>

Physical Form:

Liquid

Quantity Within Each Unit Package:

20.000 grams

Specific Usage Design:

For bonding metal, plastic and elastomeric materials; specifically formulated for difficult to bond substrates

Rated Drying Time:

20.000 seconds

Special Features:

Ethyl cyanoacrylate; low viscosity; service temperature range of minus 65 degrees f to plus 180 degrees f; 24 hour full cure time

Color:

Clear

Material:

Plastic

Supplementary Features:

20 gram bottle

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fig:

A535p0