

View Online at <https://aerobasegroup.com/nsn/8040-01-388-2930>

Physical Form:

Liquid

Quantity Within Each Unit Package:

1.000 quarts

Specific Usage Design:

For repairing graphite or glass composites used in aerospace applications

Features Provided:

Separate catalyst

Rated Drying Time:

130.000 minutes

Special Features:

Elevated temperature cure; 130 minutes at 300 degrees f or 150 minutes at 250 degrees f or 220 minutes at 200 degrees f; store at 40 degrees f or below

Color:

Purple

Material:

Plastic epoxy

Supplementary Features:

1 quart kit

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A535p0