

View Online at <https://aerobasegroup.com/nsn/8040-01-394-2022>

Physical Form:

Liquid

Quantity Within Each Unit Package:

1.000 ounces

Specific Usage Design:

For bonding materials with severely mismatched coefficients of thermal expansion

Rated Drying Time:

3.000 hours

Special Features:

Premixed and frozen; flexible; elevated temperature cure, 3 hours at 100 degrees c or 8 hours at 75 degrees c; must be shipped and stored at minus 40 degrees f or below

Color:

Amber

Material:

Plastic epoxy

Supplementary Features:

1 ounce syringe

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fig:

A535p0