

View Online at <https://aerobasegroup.com/nsn/8040-01-396-4491>

Physical Form:

Liquid

Specific Usage Design:

For bonding strain gages

Features Provided:

Separate catalyst

Rated Drying Time:

6.000 hours

Special Features:

May be used for cryogenic applications; service temperature range of minus 452 degrees f to plus 200 degrees f; elevated temperature cure; 6 hours at 125 degrees c

Color:

Clear

Material:

Plastic epoxy

Supplementary Features:

Six 10 gram resin mixing jars, one 15 ml bottle of curing agent, five calibrated pipettes, and six stirring rods

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fig:

A535p0