

View Online at <https://aerobasegroup.com/nsn/8040-01-396-8306>

**Physical Form:**

Paste

**Quantity Within Each Unit Package:**

3.000 milliliters

**Specific Usage Design:**

For electronics bonding applications

**Rated Drying Time:**

8.000 hours

**Special Features:**

Premixed and frozen; silver filled; electrically conductive; elevated temperature cure; 1 hour at 80 degrees c or 10 minutes at 200 degrees c; store at minus 40 degrees c

**Color:**

Silver

**Material:**

Plastic epoxy

**Supplementary Features:**

3 milliliter syringe

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fig:**

A535p0