

View Online at <https://aerobasegroup.com/nsn/8040-01-406-0443>

Physical Form:

Paste

Quantity Within Each Unit Package:

2.000 pounds

Specific Usage Design:

For bonding metals and ceramics in heat sink applications

Rated Drying Time:

15.000 minutes

Special Features:

Thermally conductive; elevated temperature cure, 15 minutes at 175 degrees c, 1 hour at 120 degrees c or 4 hours at 85 degrees c

Color:

Black

Material:

Plastic epoxy

Supplementary Features:

2 pound can

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fig:

A535p0