

View Online at <https://aerobasegroup.com/nsn/8040-01-446-4780>

Temperature Rating:

550.0 degrees fahrenheit

Physical Form:

Film

Quantity Within Each Unit Package:

501.000 square feet

Specific Usage Design:

For bonding composites, metals and honeycomb

Rated Drying Time:

1.000 hours

Special Features:

Modified bismaleimide; 0.10 psf weight; cures at 350 degrees f for 1 hour, post cure at 475 degrees f for 2 hours; for service temperatures up to 550 degrees f; must be shipped and stored at 0 degrees f or below

Supplementary Features:

501 square foot roll

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A535p0