

View Online at <https://aerobasegroup.com/nsn/8040-01-446-4780>

**Temperature Rating:**

550.0 degrees fahrenheit

**Physical Form:**

Film

**Quantity Within Each Unit Package:**

501.000 square feet

**Specific Usage Design:**

For bonding composites, metals and honeycomb

**Rated Drying Time:**

1.000 hours

**Special Features:**

Modified bismaleimide; 0.10 psf weight; cures at 350 degrees f for 1 hour, post cure at 475 degrees f for 2 hours; for service temperatures up to 550 degrees f; must be shipped and stored at 0 degrees f or below

**Supplementary Features:**

501 square foot roll

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fiig:**

A535p0