

View Online at <https://aerobasegroup.com/nsn/8040-01-449-9119>

**Specific Usage Design:**

Bonding abs, natural rubber and balsa

**Curing Method:**

Air dried

**Rated Drying Time:**

Between 1.000 seconds and 10.000 seconds

**Special Features:**

600 cp viscosity; 0.17 mm gap fill; 3400 psi shear tensile strength; -80 to 80 degrees c temp range; surface insensitive

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fiig:**

A535p0