

View Online at <https://aerobasegroup.com/nsn/8040-01-465-4297>

Physical Form:

Liquid

Specific Usage Design:

For filling voids, spaces, and recesses of electronic assemblies to prevent air and contamination entrapment in thermal interfaces

Features Provided:

Separate catalyst

Rated Drying Time:

72.000 hours

Special Features:

Thermally conductive; magnesium-oxide filled; room temperature or elevated temperature cure, 72 hours at 75 degrees f, 4 hours at 200 degrees f

Material:

Plastic epoxy

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A535p0