

View Online at <https://aerobasegroup.com/nsn/8040-01-465-4297>

**Physical Form:**

Liquid

**Specific Usage Design:**

For filling voids, spaces, and recesses of electronic assemblies to prevent air and contamination entrapment in thermal interfaces

**Features Provided:**

Separate catalyst

**Rated Drying Time:**

72.000 hours

**Special Features:**

Thermally conductive; magnesium-oxide filled; room temperature or elevated temperature cure, 72 hours at 75 degrees f, 4 hours at 200 degrees f

**Material:**

Plastic epoxy

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fiig:**

A535p0