

View Online at <https://aerobasegroup.com/nsn/8040-01-483-6087>

**Tempurature Rating:**

250.0 degrees fahrenheit

**End Application:**

B2 acft

**Physical Form:**

Paste

**Quantity Within Each Unit Package:**

6.000 ounces

**Curing Method:**

Air dried or heat

**Features Provided:**

Separate catalyst

**Product Name:**

Core potting material, low density, nonsage 250f

**Special Features:**

Epoxy based syntactic foam formulation w/a smooth texture. Long working time, low density, nonsag, hi compressive strength. Used for edge filling, potting fiberglass honeycomb core. Materials for horizontal core cell application. Premix and frozen are homogeneous texture, free of foreign material, lumps and coarse particles. P/n is 1110pmf, premix and frozen. Working time 60 min. Pmf shelf life unopened 90 day at -40c or below. Drying time is 7 days at 77f or 1 hr at 250f; formulated for use on plastic, epoxy

**Color:**

White or yellow

**Material:**

Plastic epoxy

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fiig:**

A535p0