

View Online at <https://aerobasegroup.com/nsn/8040-01-485-6993>

Tempurature Rating:

450.0 degrees fahrenheit

End Application:

F-22 acft

Physical Form:

Film

Specific Usage Design:

Core splice adhesive

Curing Method:

Heat

Features Provided:

Heat vulcanize feature

Rated Drying Time:

Between 2.000 hours and 4.000 hours

Product Name:

Adhesive, foaming

Special Features:

Sheet form w/liner, size 1 x 2 ft; store at zero degrees f or below; cure 1 hr at 350 degrees f

Color:

Green, light

Material:

Plastic epoxy

Supplementary Features:

Store at zero degrees fahrenheit or below, shelf life 12 months

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A535p0