

View Online at <https://aerobasegroup.com/nsn/8040-01-487-7328>

End Application:

C-17 acft, cmc

Physical Form:

Film

Curing Method:

Heat

Features Provided:

Heat vulcanize feature

Product Name:

Film, adhesive

Special Features:

Ddms2169 t2c1gb; epoxy resin film adhesive; nonwoven carrier; both sides tacky (bst); weight: 0.060 pounds per square foot; shelf life when new: 120 days when stored at 0f, 90 days when stored at 35f to 50f; shelf life is guaranteed to be at least 50 days upon receipt; total allowable out of freezer time is 10 days at 85f; cure at 250f; serviceable temperature range -70f to 180f; u/i is 36" wide; order is 2 yds; store and ship at 0f or below

Material:

Plastic epoxy

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fig:

A535p0