

View Online at <https://aerobasegroup.com/nsn/8040-01-525-9305>

End Application:

F/a-22 raptor

Physical Form:

Film

Usage Design:

For use in aerospace structures

Curing Method:

Heat

Product Name:

Fabric, s-2 glass, woven epoxy resin impregnated for structural repair applications

Special Features:

The materials shall be stored at 10 degrees f or below in the sealed vapor barrier bag, one roll per bag manufacture description of p/n 107077 is 6781gl 8552, 37%, 203 aw, 50 inch. 6781gl is 8 harness satin s2 fiberglass style 6781 woven fabric, 8552 is the epoxy resin, 37% is the resin content, 203aw is the areal weight in grams per square meter, 50 inch is the width of roll

Color:

Yellow

Supplementary Features:

After placing the prepared layup in the appropriate curing equipment, refer to specification 5ptm15-a, page 31, para 4.4.2.3.1 for curing cycle

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A535p0