

View Online at <https://aerobasegroup.com/nsn/8040-01-526-6604>

End Application:

F/a-22 raptor

Physical Form:

Film

Specific Usage Design:

Use for structural repair applications

Curing Method:

Heat

Product Name:

Tape carbon fiber epoxy resin, impregnated for structural repair applications

Special Features:

The materials shall be stored at 10 degrees f or below in the sealed vapor barrier bag, one roll per bag manufacture description of p/n 166805 is im7-g/8552, 34%, 145 aw, 12 inch. Im7-g is the carbon fiber type and sizing, 8552 isis the epoxy resin, 34% is the resin content, 5 aw is the areal weight in grams per square meter, 12 inch is the width of roll

Supplementary Features:

After placing the prepared layup in the appropriate curing equipment refer to specification 5ptmbt12, page 29, par 4.4.2.3.1 for curing cycle

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fig:

A535p0