

View Online at <https://aerobasegroup.com/nsn/8040-01-533-2031>

Physical Form:

Paste

Quantity Within Each Unit Package:

0.500 pounds

Specific Usage Design:

For electronics bonding applications

Features Provided:

Separate catalyst

Rated Drying Time:

18.000 hours

Special Features:

Nickel filled; electrically conductive; for use where exposure to salt water may be encountered; room temperature cure or elevated temperature cure, 18 hours at room temperature, 2 to 3 hours at 65 degrees c

Color:

Gray

Material:

Plastic epoxy

Supplementary Features:

1/2 pound kit

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A535p0