

View Online at <https://aerobasegroup.com/nsn/8040-01-554-0640>

End Application:

Logbow apache helicopter

Specific Usage Design:

General bonding

Curing Method:

Heat

Special Features:

Mix 100 parts resin to 85 parts catalyst by weight and schedule shall be one hour at 150 degrees and 24 hours to ambient; store in sound, unopened containers at 65 to 80f; pre-mixed and frozen shall be stored below 40f; shelf life of 6 months and premixed, frozen adhesive of 45 days; must be re-tested if past shelf life; mark each container in accordance with mil-std-129; ship adhesive in packed dry ice

Material:

Plastic

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fig:

A535p0