

View Online at <https://aerobasegroup.com/nsn/8040-01-644-9395>

End Application:

Hcons4ch3

Specific Usage Design:

To promote adhesion of windshield sealants pr-1425 and pr-1829 to windshield surfaces where crazing is a concern.

Curing Method:

Air dried

Minimum Flash Point:

12.0 degrees celsius

Rated Drying Time:

Between 30.0 minutes and 45.0 minutes

Color:

Colorless

Supplementary Features:

Do not craze acrylic or polycarbonate

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A535p0