

View Online at <https://aerobasegroup.com/nsn/9150-01-197-7693>

End Application:

Mrap buffalo mk2a2; medium mine protected vehicle - mmpv

Quantity Within Each Unit Package:

14.000 ounces, avoirdupois

Melting Point Temperature Rating:

180.0 degrees celsius

Minimum Dropping Point:

220.0 degrees celsius

Effective Temperature Range Rating:

+25.0/+1000.0 degrees celsius

Vapor Pressure Maximum Temperature Rating:

1000.0 degrees celsius

Special Features:

Oxidation resistant, 5.5 percent lithium soap, dropping point at 0 degrees f: 390 product name: marfak multipurpose 2, lithium hydroxysterate thickened; penetration, astm at 77 degree unworked: 295, penetration, astm at 77 degrees worked: 273, recommended for general automotive use where a single multipurpose grease is needed

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fig:

A41600

Mil-std (military Standard):

Mil-g-10924 spec.