NSN 9150-01-328-2552

Solid Film Lubricant - Page 1 of 1



View Online at https://aerobasegroup.com/nsn/9150-01-328-2552

Unit Package Type:
Can
Basic Ingredient:
Molybdenum disulfide
Maximum Service Tempurature Limit:
400.0 degrees fahrenheit
Special Features:
Water based; gray; liquid; silicate binder; thermally cured; cure time is 2 hours at 175 degrees f, then 2 hours at 400 degrees f; comes in
1 pint can
Shelf Life:
N/a
Unit Of Measure:
Demilitarization:
No
Fiig:
Т096-b