

View Online at <https://aerobasegroup.com/nsn/9150-01-515-4523>

Basic Ingredient:

Molybdenum disulfide

Maximum Service Temperature Limit:

750.0 degrees fahrenheit

Special Features:

Solid film lubricant; smooth, matt gray/black finish; spray dip or dip/spin application method; full cure in 24 hrs. Min at 77 deg. F or 1 hr. At 250 deg.F

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

T096-b