

View Online at <https://aerobasegroup.com/nsn/9150-01-530-1414>

End Application:

Eurofighter 2000 aircraft

Basic Ingredient:

Molybdenum disulfide

Maximum Service Temperature Limit:

500.0 degrees fahrenheit

Special Features:

Operating temp, -320 degrees f to + 500 degrees f; vehicle type, epoxy-phenolic; wear life, 496 minutes avg; color flat dark grey; applied by spray or dipping; dry film lubricant, corrosion inhibiting; chemical resistant; viscosity, 40-46 sec; flash point 44 degrees f

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

T096-b