

View Online at <https://aerobasegroup.com/nsn/9330-00-180-9641>

Fabrication Method:

Laminated

Nonmetallic Hardness Rating:

83.0 rockwell m and 116.0 rockwell m

Min. Tensile Strength (psi):

22400 pounds per square inch and 17300 pounds per square inch

Width:

Between 35.961 inches and 36.031 inches

Thickness:

Between 0.238 inches and 0.262 inches

Length:

Between 47.967 inches and 48.031 inches

Material Transparency:

Clear

Strengthening Feature Material:

Paper

Flexural Strength:

25100 pounds per square inch and 21400 pounds per square inch

Strengthening Feature:

Base or filler

Material:

Plastic, phenolic, l-p-513, type pbg

Material:

Plastic phenolic and paper

Material Specification:

L-p-513, type pbg federal specification 1st material response

Specification Or Standard:

Pbg type

Departure From Cited Designator:

As modified by lg and w

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A26800