

View Online at <https://aerobasegroup.com/nsn/9510-01-362-8642>

Fabrication Method:

Hot rolled

Length:

12.000 feet

Cross Section Outside Diameter:

6.000 inches

Basic Shape Style:

Round

Special Features:

Tensile strength: psi: 150,000 min.; yield strength: psi: 130,000 min.; rockwell hardness: c22; elongation: 14 percent; for use in the manufacturing of highly stressed aircraft parts requiring high hardenability

Heat Treatment:

Annealed

Material:

Steel, mil-s-6758

Material:

Steel comp 4130

Material Specification:

Mil-s-6758 military specification 1st material response

Specification Or Standard:

4340 class

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A13100

Mil-std (military Standard):

Mil-s-6758 spec.