

View Online at <https://aerobasegroup.com/nsn/9525-00-840-7647>

Length:

1600.000 feet

Cross Section Outside Diameter:

0.015 inches

Basic Shape Style:

Round

Min. Tensile Strength (psi):

90000 pounds per square inch

Heat Treatment:

Quarter hard

Material:

Copper, qq-c-533, alloy 172 or copper, qq-c-530, alloy 173

Material:

Copper alloy 172 or copper, qq-c-530, alloy 173

Material Specification:

Qq-c-533, alloy 172 federal specification 1st material response

Specification Or Standard:

One quarter hard temper

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fig:

A13100