

View Online at <https://aerobasegroup.com/nsn/9530-00-060-4468>

Fabrication Method:

Any acceptable

Length:

Between 8.000 feet and 12.000 feet

Cross-sectional Thickness:

0.6250 inches

Cross-sectional Width:

3.000 inches

Basic Shape Style:

Flat

Edge Type:

Any acceptable

Heat Treatment:

Half hard

Material:

Copper alloy 342 or copper alloy 353

Material Specification:

Qq-b-613, alloy 342 federal specification 1st material response and qq-b-613, alloy 353 federal specification 2nd material response

Specification Or Standard:

342 composition or 353 composition and bar form and half-hard temper

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A13100