

View Online at <https://aerobasegroup.com/nsn/9530-00-097-0788>

Fabrication Method:

Permanent mold cast

Length:

Between 8.000 feet and 12.000 feet

Cross Section Outside Diameter:

3.000 inches

Basic Shape Style:

Round

Criticality Code Justification:

Zzzx

Heat Treatment:

As cast

Material:

Copper alloy, qq-c-390, alloy 903

Material:

Copper alloy 903

Material Specification:

Qq-c-390, alloy 903 federal specification 1st material response

Surface Condition:

Polished

Specification Or Standard:

D5 composition and as cast condition and 3 type

Departure From Cited Designator:

Material controlled iaw navsea 0948-lp-045-7010 material control standard for level i items

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A13100