

View Online at <https://aerobasegroup.com/nsn/9530-00-411-2251>

Fabrication Method:

Extruded

Length:

Between 8.000 feet and 12.000 feet

Basic Shape Style:

Square

Cross-sectional Width Across Flats:

1.000 inches

Heat Treatment:

T-651 solution heat treated and stress relieved by stretching

Material:

Aluminum alloy 6061 or aluminum alloy 6062

Material Specification:

Qq-a-200/8 federal specification 1st material response

Departure From Cited Designator:

As modified by heat treatment

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fig:

A13100