

View Online at <https://aerobasegroup.com/nsn/9535-00-167-2131>

Fabrication Method:

Any acceptable

Width:

8.000 inches

Length:

24.000 feet

Cross-sectional Thickness:

0.0250 inches

Cross-sectional Width:

8.000 inches

Basic Shape Style:

Solid

Edge Type:

Any acceptable

Weight Per Unit Measure:

17.640 pounds per linear foot

Min. Tensile Strength (psi):

Not rated

Minimum Yield Strength:

Not rated

Heat Treatment:

Half hard

Material:

Brass, qq-b-626, comp 11

Material:

Copper alloy 260 or copper alloy 262 or copper alloy 268 or copper alloy 270 or copper alloy 272 or copper alloy 274 or copper alloy 280 or copper alloy 330 or copper alloy 331 or copper alloy 332 or copper alloy 335 or copper alloy 340 or copper alloy 342 or copper alloy 344 or copper alloy 345 or copper alloy 347 or copper alloy 348 or copper alloy 350 or copper alloy 353 or copper alloy 356 or copper alloy 360 or copper alloy 370 or copper alloy 462 or copper alloy 464 or copper alloy 465 or copper alloy 466 or copper alloy 467 or copper alloy 482 or copper alloy 485

Material Specification:

Qq-b-626, comp 11 federal specification 1st material response

Specification Or Standard:

11 composition and half-hard temper

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fig:

A13100