

View Online at <https://aerobasegroup.com/nsn/9535-00-277-7430>

**Fabrication Method:**

Cold rolled

**Width:**

36.000 inches

**Length:**

8.000 feet

**Cross-sectional Thickness:**

0.0780 inches

**Basic Shape Style:**

Round

**Perforation Diameter:**

0.375 inches

**Perforation Center To Center Distance Along Upward Slope:**

0.750 inches

**Weight Per Unit Measure:**

2.760 pounds per square foot

**Min. Tensile Strength (psi):**

70000 pounds per square inch

**Minimum Yield Strength:**

28000 pounds per square inch

**Special Features:**

0.750 in. Perforation center to center distance along vertical axis

**Heat Treatment:**

Annealed

**Material:**

Nickel, qq-n-281, class a

**Material:**

Nickel alloy 400

**Material Specification:**

Qq-n-281, class a federal specification 1st material response

**Specification Or Standard:**

Condition annealed and staggered centers and type 6

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fiig:**

A13100

**Mil-std (military Standard):**

Mil-s-12875 spec.