

View Online at <https://aerobasegroup.com/nsn/9535-00-288-3662>

Fabrication Method:

Hot rolled

Width:

48.000 inches

Length:

12.000 feet

Cross-sectional Thickness:

0.0320 inches

Edge Type:

Any acceptable

Cladding Thickness:

0.002 inches

Perforation Elongation Length:

0.531 inches

Perforation Elongation Width:

0.219 inches

Min. Tensile Strength (psi):

59000 pounds per square inch

Minimum Yield Strength:

39000 pounds per square inch

Heat Treatment:

T-3 solution heat treated

Material:

Aluminum alloy, qq-a-250/5

Material:

Aluminum alloy 2024

Material Specification:

Qq-a-250/5 federal specification 1st material response

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fig:

A13100