

View Online at <https://aerobasegroup.com/nsn/9535-00-640-4225>

Fabrication Method:

Rolled

Width:

48.000 inches

Length:

12.000 feet

Cross-sectional Thickness:

0.1600 inches

Basic Shape Style:

Solid

Cladding Thickness:

0.0040 inches

Min. Tensile Strength (psi):

73000 pounds per square inch

Minimum Yield Strength:

63000 pounds per square inch

Heat Treatment:

T-6 solution heat treated

Material:

Aluminum alloy, qq-a-250/13

Material:

Aluminum alloy 7075 and aluminum alloy 7072

Material Specification:

Qq-a-250/13 federal specification 1st material response

Specification Or Standard:

Alloy 7075 alclad and temper t6

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A13100