

View Online at <https://aerobasegroup.com/nsn/9535-00-857-1818>

**Fabrication Method:**

Rolled

**Width:**

Between 6.000 inches and 8.000 inches

**Length:**

Any acceptable

**Cross-sectional Thickness:**

0.0250 inches

**Cross-sectional Width:**

Between 6.000 inches and 8.000 inches

**Basic Shape Style:**

Solid

**Edge Type:**

Square

**Weight Per Unit Measure:**

Any acceptable

**Min. Tensile Strength (psi):**

Not rated

**Minimum Yield Strength:**

Not rated

**Heat Treatment:**

Soft annealed

**Material:**

Brass, qq-b-613, comp 11

**Material:**

Copper alloy 260 or copper alloy 262 or copper alloy 268 or copper alloy 270 or copper alloy 272 or copper alloy 274 or copper alloy 280 or copper alloy 330 or copper alloy 331 or copper alloy 332 or copper alloy 335 or copper alloy 340 or copper alloy 342 or copper alloy 344 or copper alloy 345 or copper alloy 347 or copper alloy 348 or copper alloy 350 or copper alloy 353 or copper alloy 356 or copper alloy 360 or copper alloy 370

**Material Specification:**

Qq-b-613, comp 11 federal specification 1st material response

**Specification Or Standard:**

11 composition and strip form and soft annealed condition

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fiig:**

A13100